

EPIGEN CHEMPROOF 4028 & 4029 FC GRADES

EPIGEN CHEMPROOF 4000 SERIES SUPPLEMENTARY INFORMATION

SPD -194
REV 1-0994

PRODUCT	4028FC	4029FC
COLOUR	Cream	Cream
CONSISTENCY	Viscous liquid	Thixotropic liquid
PACK SIZE	4.7kg	7.5kg
MIXING RATIO	4 parts A to 1 part B	4 parts A to 1 part B
SPECIFIC GRAVITY	1.1 - 1.2	1.55 - 1.65
POT LIFE (500gm @ 25°C)	20 minutes	20 minutes
NON VOLATILE MATTER	100%	100%
CURE TIME (@ 25°C)	1-2 hours	1-2 hours
RECOMMENDED MODE OF APPLICATION	Plural mix spray apparatus; Trowel incorporating aggregate; small volume hand brushing, rolling, or squeegee.	Plural mix spray apparatus; Trowel incorporating aggregate; small volume hand brushing, rolling, or squeegee.
RECOMMENDED AGGREGATE ADDITION TO EVERY 1 PART RESIN	3 pts 16/30 & 2 pts 30/50 silica sand to obtain a trowellable mortar	1½ pts 30/50 silica sand to obtain a trowellable render
COVERAGE INCORPORATING AGGREGATE	19 kg of prepared mortar will coat 1m ² @ 10mm thick	6 kg of prepared render will coat 1m ² @ 3mm thick